

Non Skid

Technical Data Sheet: 907-41
A5003 / A5007

-
- 1. Introduction** ALEXSEAL Non Skid is specifically developed to achieve non-skid textures.
- 2. Range of application** Surfaces where anti-skid properties are required.
- 3. Color** Transparent
- 4. Coverage** See TDS for ALEXSEAL Premium Topcoat 501/Acrylic Topcoat X
- 5. Substrate pre-treatment** See TDS for ALEXSEAL Premium Topcoat 501/Acrylic Topcoat X
- 6. Trade names & Packaging**
- | | | |
|-------|--------------------------|--------------------|
| A5003 | ALEXSEAL Non Skid Fine | 1/2 Gal (1.98 lb.) |
| A5007 | ALEXSEAL Non Skid Coarse | 1/2 Gal (1.98 lb.) |
- 7. Mixing ratio** See TDS for ALEXSEAL Premium Topcoat 501/Acrylic Topcoat X
- The degree of skid texture can be varied by mixing ALEXSEAL Non Skid Fine and ALEXSEAL Non Skid Coarse. To receive an optimal effect, testing previously on a small area is recommended.
- Example for a medium grade of non-skid (most preferred):
1 Part ALEXSEAL Non Skid Coarse + 1 Part ALEXSEAL Non Skid Fine
- Spray: For 1 gallon of mixed topcoat add 1 – 1.5 Quart ALEXSEAL Non Skid
- Brush and Rolling: For 1 gallon of mixed topcoat add 0.8 - 1 Quart ALEXSEAL Non Skid
- Sprinkling: As desired
- 8. Application** See TDS for ALEXSEAL Premium Topcoat 501/Acrylic Topcoat X
- Application by Spraying: Add ALEXSEAL Non Skid to the mixed topcoat in the quantity stated above and apply by cross coat spraying. (Fluid Nozzle Size of 1.5 – 1.8 mm, 0.059 to 0.07)
- Application by brush/rolling: Add ALEXSEAL Non Skid to the mixed topcoat in the quantity stated above and apply by brush or rolling.
- Sprinkling: Apply the mixed topcoat to the designated area by brush or roller to achieve a sticky layer. Make small holes in the transparent plastic lid of the container. ALEXSEAL Non Skid can be sprinkled by means of this salt litter container on the paint film. Allow to 10 to 20 minutes to dry firmly into the topcoat, until the paint film is slightly dry but still sticky. Apply additional coats of topcoat. Some applications may require two finish coats.
- 9. Pot life and Drying** Optimal application environment range:
Min. 15°C (60°F) 40% RH
Max. 30°C (85°F) 80% RH
See TDS for ALEXSEAL Topcoat

Professional Use Only

Page 1 of 1

The information contained in this data sheet is based on our level of research and development. Revisal by the user with regard to the intended aim is necessary due to the diverse processing and application possibilities. Any liability on part of Mankiewicz for faulty applications and / or improper use is expressly excluded. The processing of the product must be fully documented by means of a paint application protocol.