

## Bright Color Antifouling

- The brightest colors including the blackest black and the whitest white in bottom paints
- Excellent, multi-season, dual biocide antifouling protection under all conditions
- Hybrid technology incorporates all the benefits of abrasives and hard paints
- Hard, smooth surface withstands trailering and is easily burnished to a racing finish



All colors available in quarts and gallons

Note: Color differences may occur between actual and color chips shown



## Technical Information



**Finish:** Flat  
**Solids by Weight:** 83%  
**Coverage:** 440 ft<sup>2</sup>/gal.  
**VOC:** 330 grams/liter (max)  
**Biocide:** Cuprous Thiocyanate...25.0%  
 Zinc Pyrithione...2.80%  
**Flash Point:** 110°F (SETA)  
**Application Method:** Brush, roller, airless or conventional spray.  
**Maximum Roller Thickness:** 3/16"  
**Number of Coats:** 1 minimum per season with additional coats for extended service  
**Wet Film Thickness:** 3.1 mils  
**Dry Film Thickness:** 2 mils  
**Application Temp:** 50° F. Min. / 90°F. Max.  
**Thinner:** 120 Brushing Thinner, 121 Spraying Thinner, or 120VOC Thinner  
**Dry Time\*:** (hours) Substrate temperature must be at least 5°F above dew point.

	To Recoat	To Launch
90°F	4	16
70°F	8	24
50°F	16	48

\*The above dry times are minimums. Vivid may be recoated after the minimum time shown. There is no maximum dry time before launching.

Now you can have the brightest colors, the blackest black and the whitest white available in a bottom paint. Vivid provides excellent multi-season, dual biocide antifouling protection under all conditions. Vivid's new hybrid technology incorporates all the benefits of both abrasive and hard paints in one superior product. Its hard, smooth surface withstands trailering and is easily burnished to a high performance racing finish. Applied in very thin coats using a 3/16" or less nap roller, Vivid resists build up and can be hauled and launched without loss of protection. When used over the recommended priming system Vivid can safely be used on aluminum hulls and outdrives. The perfect antifouling choice for any boat.

## Application Systems and Tips

Vivid is easily applied by brush, roller or spray. When rolling, use only a high-quality short nap (maximum 3/16" nap) roller cover. Apply using thin coats; over-application of this product will virtually assure inadequate coating performance. Mix paint thoroughly to ensure ingredients are evenly dispersed throughout the can. All surfaces must be clean, dry and properly prepared prior to painting. Do not apply Vivid directly on aluminum hulls or outdrives without properly priming first.

## Previously Painted Surfaces:

Vivid may be applied over most aged hard antifouling coatings. Consult the Pettit Antifouling Compatibility Chart for specific recommendations. Old tin copolymers must be removed completely or sealed with Pettit 6627 Tie-Coat Primer before applying this product. The paint systems outlined below contain references to other products; please read and understand the label and/or Technical Bulletin for these products as well, to ensure that they are used properly.

If the previous coating is in good condition, thoroughly sand with 80-grit sandpaper then solvent clean with Pettit 120 or 120VOC Thinner to remove residue. Apply two thin finish coats of Vivid. If the previous coating is soft or in poor condition, remove to the bare surface by sanding or using paint remover. Proceed with appropriate bare system as described below.

## Bare Fiberglass:

All bare fiberglass, regardless of age, should be thoroughly cleaned with Pettit 92 Bio-Blue Hull Surface Prep or de-waxed several times with Pettit D95 Dewaxer. Proceed with either Sanding Method or one of the Non-Sanding Methods below.

**Sanding Method** - After the surface has been de-waxed, sand thoroughly with 80-grit production paper to a dull, frosty finish and rewash the sanded surface with Pettit 120 or 120VOC Thinner to remove sanding residue. Then apply two thin finish coats of this product, following application instructions. Careful observation of application instructions will help ensure long-term adhesion of this and subsequent years' antifouling paint.

**Non-Sanding Method** - To eliminate the sanding method, two alternative methods are available:

1) Thoroughly clean, de-wax, and etch the surface with Pettit 92 Bio-Blue Hull Surface Prep using a medium Scotch-Brite® pad in a swirling motion or wash the fiberglass at least three times using Pettit D95 Dewaxer. Then apply one thin coat of Pettit 6998 Skip-Sand Primer. Use a 3/16" or less nap when applying by roller. Consult the primer label for complete application and antifouling top-coating instructions. Apply two thin finish coats of Vivid.

2) Thoroughly clean, de-wax, and etch the surface with Pettit 92 Bio-Blue Hull Surface Prep using a medium Scotch-Brite® pad in a swirling motion. Thoroughly rinse all residue from the surface and let dry. Then apply one coat of Pettit 4740/4741 H2-Prime Epoxy Primer or Pettit Protect High Build Epoxy Primer (4700/4701 or 4100/4101). Consult the primer label for complete application and antifouling top-coating instructions.

Apply two thin finish coats of Vivid. See Pettit Protect User Manual for complete detailed instructions.

## Barrier Coat:

Fiberglass bottoms potentially can form osmotic blisters within the gelcoat and into the laminate. To render the bottom as water impermeable as possible, prepare the fiberglass surface as mentioned above (sanding method) then apply two or three coats of Pettit Protect High Build Epoxy Primer (4700/4701 or 4100/4101), per label directions. Apply two thin coats of Vivid. See Pettit Protect User Manual for complete detailed instructions.

## Blistered Fiberglass:

See Pettit Protect User Manual for complete detailed instructions.

## Bare Wood:

Bare wooden hulls should be sanded thoroughly with 80-grit sandpaper and wiped clean of sanding residue using Pettit 120 or 120VOC Thinner. Apply a coat of Vivid thinned 25% with Pettit 120 or 120VOC Thinner, allow an overnight dry, lightly sand and wipe clean. Apply two thin finish coats of Vivid.

## Bare Steel and Cast Iron\*:

Remove loose rust and scale from the metal surface by sandblasting or wire brushing. Immediately clean the surface using a vacuum or fresh air blast. Apply two coats of Pettit 6980 Rustlok Steel Primer, allowing each to dry only one to two hours prior to over coating. Follow by two coats of Pettit Protect High Build Epoxy Primer (4700/4701 or 4100/4101) per label directions. If fairing is required, apply Pettit 7050 EZ-Fair Epoxy Fairing Compound between the two coats of Pettit Protect High Build Epoxy Primer. Apply two thin finish coats of Vivid. See Pettit Protect User Manual for complete detailed instructions.

## Stainless Steel, Bronze, Lead, and Non-Aluminum Alloys \*:

Abrade surface to bright metal; clean off residue using Pettit 120 or 120VOC Thinner. Apply one thin coat of Pettit 6455/044 Metal Primer; allow to dry two hours. Apply two coats of Pettit 6627 Tie-Coat Primer, per label directions. Let the second coat of Pettit 6627 Tie-Coat Primer dry at least four hours and apply two thin finish coats of Vivid.

## Bare Aluminum:

**Basic Method** - If the surface to be painted is smooth aluminum, apply one thin coat of Pettit 6455/044 Metal Primer and allow to dry for two hours. Read and follow carefully the instructions for application and top-coating on the Pettit 6455/044 primer label. Apply two coats of Pettit 6627 Tie-Coat Primer, per label directions, prior to applying the two thin finish coats of Vivid.

**Best Method** - For maximum corrosion resistance, sandblast to clean, bright metal and remove blasting residue with clean, dry compressed air or a clean brush. Immediately apply two coats of Pettit 4400/4401 Aluma Protect Epoxy Primer, followed by two coats of Pettit Protect High Build Epoxy Primer (4700/4701 or 4100/4101), per label directions. Apply two thin finish coats of Vivid.

\*These are simplified systems. Pettit offers Technical Bulletins containing detailed instructions for most application systems. Please consult your Pettit Representative or the Pettit Technical Department for more complex, professional systems. Always read the labels or Product Data Sheets for all products specified herein before using.

## Application Information



The active ingredients in Vivid can settle over time, especially if the paint has been on the shelf for several months. It is necessary to thoroughly mix the paint before using. If possible, shake the can of paint on a mechanical paint shaker. Before using, check the sides and bottom of the can to make sure all of the pigment has been mixed in. If mixing is going to be done with a wooden paddle or an electric drill mixer, pour off half of the liquid from the top of the can into another can and then properly mix in any settled pigment; then remix the two parts together thoroughly. Adhere to all application instructions, precautions, conditions, and limitations to obtain optimum performance. Refer to individual labels and tech sheets for detailed instructions when using associated products, etc. When spraying, do not thin Vivid more than 5% (6 ounces per gallon) or inadequate paint film thickness will occur and premature erosion of the finish will be likely. Do not apply Vivid in thick films or in more than two coats, as poor adhesion may result. When applying by roller, use a short nap (3/16" maximum) roller cover.

## Surface Preparation:

Coating performance, in general, is proportional to the degree of surface preparation. Follow all recommendations very carefully, avoiding any shortcuts. Inadequate preparation of surfaces will virtually assure inadequate coating performance. The surface to be painted should be dry, clean and free of any contaminants. It should be properly prepared by following the recommended systems below. When sanding old antifouling paint, always wear Personal Protective Equipment (PPE) to prevent the inhalation of sanding dust.

## Maintenance:

No antifouling paint can be effective under all conditions of exposure. Man-made pollution and natural occurrences can adversely affect antifouling paint performance. Extreme hot and cold water temperatures, silt, dirt, oil, brackish water and even electrolysis can ruin an antifouling paint. Therefore, we strongly suggest that the bottom of the boat be checked regularly to make sure it is clean and that no growth is occurring. The self-cleaning nature of the coating is most effective when the boat is used periodically. Boats and vessels should not be scrubbed or cleaned for the first six months in the water, and at intervals of not less than three months thereafter. Burnishing of the surface to create a slicker finish should be done with 400-600 grit wet-or-dry sandpaper after the coating has dried for seven (7) days.