



APPLICATION NOTE - SR001

Cold Weather Application

Silent Running is best applied with the ambient, material and substrate temperature in the range of 65 - 85 degrees F.

Lower temperatures will result in longer dry times, and Silent Running should be applied in thinner coats as sagging may occur.

Lower temperature coats should not exceed 12 - 15 mils in thickness, if there is any question, a small test area should be coated. Wait 20-30 minutes to observe the results.

Remember, just because the air temperature is in the acceptable range, material and substrate may not be. Allow sufficient time for both material and substrate to reach an acceptable temperature if they have been exposed to cold.

If there are any question concerning the application of Silent Running, please contact us at the numbers below.

Current Inc.
30 Tyler Street
PO Box 120183
East Haven, CT 06512

Phone: 203-469-1337
Toll free: 877-436-6542
Fax: 203-467-8435