



## APPLICATION NOTE - SR004

### Finishing

To get the best surface finish, spray application of Silent Running works the best.

Silent Running can very easily be sprayed at a thickness of 12-15 mils per coat.

If rolling Silent Running on, follow up with a fine bristle or foam brush to lightly tip off the stippling left behind by the roller.

If brushing on, again, very lightly go over the surface to smooth out the brush marks. Be careful as too much brushing will thin the surface coating reducing the amount applied.

If there are any question concerning the application of Silent Running, please contact us at the numbers below.

Current Inc.  
30 Tyler Street  
PO Box 120183  
East Haven, CT 06512

Phone: 203-469-1337  
Toll free: 877-436-6542  
Fax: 203-467-8435